

Product Data Sheet

SUMITOMO POLYETHYLENE LDPE

L705

Low Density, Extrusion Coating

Applications	Extrusion coating for OPA/OPP film, kraft paper, aluminium, and PE woven cloth.
Characteristics	Produced using autoclave process, easy processing, excellent neck-in property, good processability, adhesion to base material, and sealing property. Contains no thermal stabiliser, slip, or antiblock additives.
Typical Processing Conditions	Extrusion temperature : 280°C - 340°C Chill roll temperature : 20°C - 40°C Air gap : 70mm - 150mm

Typical Properties

Physical		Value	Unit	Method
Melt Flow Rate	2.16kg	7	g/10min	ISO 1133
Density		0.919	g/cm ³	ISO 1183
Mechanical		Value	Unit	Method
Tensile Strength	at Break	14	MPa	ASTM D638
Tensile Elongation	at Break	550	%	ASTM D638
Flexural Modulus		165	MPa	ASTM D747
Thermal		Value	Unit	Method
Vicat Softening Temperature		86	°C	ASTM D1525
Melting Temperature		106	°C	DSC, Internal
Other		Value	Unit	Method
ESCR		1.9	hour	ASTM D1693

The values shown are typical values measured on the product and are not to be considered as guaranteed specifications, actual test results may vary
Test pieces preparation method : compression, test speed : 200mm/min

Manufacturer

L705 is manufactured in Saudi Arabia by Rabigh Refining & Petrochemical Co. (Petro Rabigh).

The certification on ISO 9001, ISO 14001, and OHSAS 18001 is in progress and will be completed soon after commercial production.

Regulatory Compliances

Evaluation on common regulatory compliances on L705 will be verified by accredited third party laboratories soon after commercial production.

Please contact your nearest SCA representative for more information.

Storage and Handling

L705 is supplied in 25kg bags or in bulk containers. It is advisable to store in a well-ventilated storage facility, protected from rain, direct exposure to sunlight, temperature, and dust.

Moisture may accumulate inside the packaging if there is a significant fluctuation in ambient temperature and high relative humidity. If this occurs, customer is strongly advised to dry the resin prior to use. Direct exposure to sunlight and excessive ambient temperature may affect the properties, appearance, and odour characteristic of the resin. Please refer to the Safety Data Sheet (SDS) for information regarding industrial health and safety issues.

Disposal and the Environment

SCA prioritises environmental management in all our operations in responsibility and respect towards the community and the environment.

Unmodified L705 is readily recyclable, both for reuse via reprocessing and for energy reclamation through incineration. If disposed in landfills, our products, which are inert materials, do not pose pollution risks since they do not generate gaseous or liquid emissions.

Office Locations**SUMITOMO CHEMICAL ASIA PTE LTD**

3 Fraser Street, #07-28 DUO Tower, SINGAPORE 189352

Phone +65 6303 5188

Fax +65 6298 9621

Web Site www.sumitomo-chem.com.sg

SUMIKA PLASTICS AND CHEMICALS TRADING (SHANGHAI) CO., LTD.

Unit 46-07 Grand Gateway II, No.3 Hongqiao Road, Xu Hui District, Shanghai, CHINA 200030

Phone +86 21 6448 2255

Fax +86 21 6407 7365

SUMIKA PLASTICS AND CHEMICALS TRADING (SHANGHAI) CO., LTD., GUANGZHOU BRANCH

Room 6404, Office Building, CITIC Plaza, No.233, North Tianhe Road, Guangzhou City, CHINA 510613

Phone +86 20 3877 3577

Fax +86 20 3877 3511

SCA SOUTH ASIA PETROCHEMICALS PRIVATE LIMITED

Private Office No. 218, DBS Business Center, FF, World Trade Tower, Barakhamba Lane, Connaught Place, New Delhi 110001, INDIA

Phone +91 11 4050 9218

Fax +91 11 2341 4740

SUMITOMO CHEMICAL EUROPE S.A./N.V.

Woluwelaan, 57, B-1830 Machelen, BELGIUM

Phone +32 2 251 0650

Fax +32 2 251 2991

Web Site sumitomochemicaleurope.eu

SUMITOMO CHEMICAL EUROPE N.V.

Turkey Liaison Office, Barbaros Mah. Cigdem Sok. No:1, Agaoglu My Office K:10, D:44-45, 34746 Bati Atasehir, Istanbul, TURKEY

Phone +90 216 680 3334

Fax +90 216 680 1012

Disclaimer

All information contained in this document is provided in good faith and its sole purpose is to provide information regarding SCA's polymer products. This product catalogue is provided on an "as is" basis. SCA makes no representation, warranty, express or implied and assumes no liability as to the accuracy or completeness of any of the information contained in this product catalogue. The values shown are purely values measured on the product and are not to be considered as guaranteed specifications. Any information on this product catalogue should not be considered as a recommendation. Customer is responsible to ensure that SCA materials, whether used alone or mix with other materials, are suitable for the intended application. SCA expressly disclaims for any and all liability, including direct and indirect loss, consequential loss or damages based on or relating to the use or errors of and omissions of such information in this product catalogue. Information contained herein is NOT intended to announce product availability anywhere in the world. Please contact your nearest SCA representative for more detailed information.